

Property	Average Value
ASTM D1056 (2000)	2A2 C
Density	130-170 kg/m ³
Compression Deflection 25% (35-63)	45 kPa
Compression Deflection 50% (80-160)	110 kPa
Shore Hardness '00' Scale	40-45
Elongation – Min	>180 %
Temperature Range (Constant)	-30 to +100 °C
Temperature Range (Intermittent)	+120 °C
Water Absorption	<5 % Vol
Tensile Strength	> 6.2 kg/cm ² (608 kPa)
Flame Resistance	FMVSS302 Self Extinguishing
Environmental Protection	CFC & HCFC Free